



Technical Data Sheet
PE LL09200 FE
Linear Low-Density Polyethylene

PRODUCT DESCRIPTION

LL09200 FE is a butene linear low-density polyethylene. Films produced from this resin show excellent puncture resistance, high tensile strength and good sealing performance.

TYPICAL APPLICATIONS

LL09200 FE is recommended for the production of heavy duty sacks, agricultural films, liners, carrier bags, frozen food bags, lamination and coextruded films and industrial packaging. It is suitable for blending with other polyethylene resins, such as LDPE or HDPE resins.

Properties	Conditions	Method	Typical values*	Units
Resin properties				
Melt Flow Rate	190 °C/2.16 kg	ISO 1133-1	0.9	g/10 min
Density		ISO 1183	0.920	g/cm ³
Properties measured on 38 µm film**				
Tensile Strength at Break	MD/TD	ISO 527-1	44/40	MPa
Tensile Stress at Yield	MD/TD	ISO 527-1	11/12	MPa
Elongation at Break	MD/TD	ISO 527-1	800/850	%
Tear Strength	MD/TD	ASTM D1922	160/360	g/25 µm
Dart Drop Impact Strength		ASTM 1709	150	g
Thermal				
Vicat Softening Temperature	10 N	ISO 306	100	°C

*The values given are typical values measured on the product. These values should not be considered as specification.

**Properties were measured on film extruded at a blow up ratio 2:1 with a melt temperature of 225 °C.

REACH Statement

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered.

PJSC «Sibur Holding» (and its subsidiaries) is committed to fully respect REACH legislation and to use only REACH compliant raw materials.

Safety

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications. To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information. PJSC «Sibur Holding» (and its subsidiaries) makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of any PJSC «Sibur Holding» (and its subsidiaries) product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.